

LOTADER® 9304T

LOTADER® 9304T is a random ethylene-vinyl acetate-maleic anhydride terpolymer (EVA-MAH).

- As an ethylene copolymer, LOTADER® 9304T is compatible with PE in all proportions, and with most ethylene copolymers.
- Vinyl acetate brings softness, flexibility, and polarity while maleic anhydride brings reactivity, leading to versatile adhesive properties to polar and non-polar substrates.
- As a result of high-pressure polymerization in tubular reactor, LOTADER® 9304T also exhibits high transparency (low haze).

LOTADER® 9304T is compatible with most tackifying resins and waxes and can be used in hot melt adhesives formulations. LOTADER® 9304T is also suitable to produce thermo-adhesive films for solid substrates like PA, PET & PU films, aluminum foils, fiber mats, foams... LOTADER® 9304T can also be used as a tie layer between polyethylene and polyamide in blown film co-extrusion.

Typical Properties

	Test Method	Unit	Typical value
Melt Index (190°C / 2.16 kg)	ISO 1133	g/10min	7.5
Vinyl Acetate content	FTIR (Internal Method)	% wt.	25
Maleic Anhydride content	FTIR (internal method)	%	0.16
Melting point	ISO 11357	°C	80
Density	ISO 1183 / ASTM D792	g/cm ³	0.94
Vicat softening temperature (10N) ¹	ISO 306	°C	49
Tensile strength at break ¹	ISO 527 / ASTM D638	MPa	26
Elongation at break ¹	ISO 527 / ASTM D638	%	700
Hardness Shore A ¹	ISO 868 / ASTM D2240		82
Ring & Ball temperature	ASTM E28	°C	150

¹: On compression molded samples.

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof and cannot be used as product specifications. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, SKFP expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN.

The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement. See SDS for Health & Safety Considerations.

Processing

LOTADER® 9304T can be processed on most conventional equipment used for thermoplastics. It is recommended to avoid overheating above 230°C and to purge the equipment after a run is completed.

Storage, Handling & Safety

LOTADER® 9304T should be stored in a ventilated area, away from heat, humidity and direct sunlight. Improper storage conditions may cause degradation and could have consequences on physical properties of the product.

Safety data sheet as well as information on handling and storage of LOTADER® 9304T are available upon request to your SK Functional Polymer representative or at www.sk-fp.com.

Shelf Life

Three years from the date of delivery, in unopened packaging. For any use above this limit, please refer to our technical services.